

TechGrid – TGU - 100


PRODUCT DATASHEET



TechGrid U series are uniaxial knitted polyester geogrids, with a polymeric coating engineered for demanding soil reinforcement applications. The high tenacity polyester yarns are formed into a dimensionally stable grid structure with uniform apertures, using an advanced weft insertion warp knitting process, which is then given a tough and durable polymeric coating to enhance dimensional stability, resistance to installation damage and durability.

Physical Properties:	Units		TGU-100	Test Method
Composition	Woven filament, high tenacity, polyester yarns			
Tensile Strength (Ultimate) ¹	MD	kN/m	≥ 100	EN-ISO-10319
	CD	kN/m	≥ 30	
Elongation (@ Ultimate ± 2%)	MD	%	10	EN-ISO-10319
	CD	%	10	
Reduction Factor (RF) and factor of safety (f _s) for calculation of MD Long-term Design Strength (LTDS):				
Creep (RF _{CR}) – 120 years design life at 20°C temperature			1.45	EN-ISO
Creep Limited Strength		kN/m	69.0	
Installation damage (RF _{ID})	Sand/silt/clay		1.02	
Partial Factor - environmental effect, pH = 5 to 9			1.07	
Factor of Safety for 120 years (f _s)			1.09	
LTDS – 120 YEARS: Sand/silt/clay for pH = 5 to 9		kN/m	58.0	
Aperture size (Tolerance ± 2mm)	30mm x 23mm			
Roll Width x Length	5.1m x 100m			

1. Average (typical) Value obtained in accredited laboratories.



To ensure this document contains the most up-to-date technical information available go to [fibertex.com](https://www.fibertex.com)

+27 31 736 7100 | salesza@fibertex.com | [fibertex.com](https://www.fibertex.com)